

AFA & COLOUR SOLVENT-FREE EPOXY COATING

DEFINITION

COLOURS

GLOSSINESS SOLIDS

SPECIFIC GRAVITY

APLICATION

THINNER

DRYING PERIOD

AMBALAGE

:Solventless epoxy polyamide resin based, two component and glossy enamel resistant against chemical and physical effects.

:All colours in the Solvent-Free Epoxy Coating catalogue are available on order.

:Glossy.

:Depending upon the colour, 50-60 % (Including the hardener)

:Depending upon the colour, 1.10-1.32 gr/cc

:2 Parts of paint should be added to 0,6 part of hardener in terms of weight, and mixed thoroughly. This mixture should be consumed within 14-16 hours as it has a life span of about 14-16 hours and starts to jellify at the and of the said period.

:Solvent-Free Epoxy Coating should only be thinned by using its

Special thinner, AFA Epoxy Thinner.

:At 20°C, Solvent-Free Epoxy Coating completes its surface drying in 1.5-2 hours and becomes dry to the touch in 20-22 hours. The complete ossification period rendering the paint resistant against chemical effects is 6-7 days after application. In order to accelerate drying and ossification, the surface could be oven dried for 1 hour at 80°C.

:1. Komponent 12 Kg

2. Komponent (Sertleştirici) 6 KG

^{*}Please consult our technical service department for details which are not sufficient the technical specifications. **Technical modifications reserved.**